

GYLON[®] Style 3501-E

High performance PTFE gasketing

Description

GYLON[®] Style 3501-E (brick red) is a high performance gasketing material made of multi-layered PTFE for permanent resilience. It's the first choice for universal applications in the chemical and petrochemical industries.

GYLON[®] Style 3501-E is a modified PTFE gasketing material and optimized for the European market.



Main Segments

» Metal Industry
» Petrochemical Industry
» Chemical Industry

Certificates/Declarations*

» FDA
» BAM (Only valid for gas)
» TA – Luft + Blow-out Proof
» Phthalat free
» Silicone, BSE, TSE & ADI free
» DIN EN 13555 values

Key Benefits

» 20 N/mm ² minimum load (160 N/mm ² maximum load)
» Wide temperature range
» Stopped cold flow
» High resilience
» High pressure & vacuum duties
» Excellent chemical resistance**
» Available with inner-/outer eyelet
» Good electrical insulating properties*
» Unlimited shelf-life
» Weather and UV resistant

Features*

» Temperature: -268 °C to +260 °C	
» Pressure: up to 83 bar	
» Shore hardness: D68	
» Available Thicknesses: 0.8mm, 1.0mm, 1.6mm, 2.0mm, 3.2mm, 4.8mm, 6.4mm (More thicknesses on request)	
» Compressibility (ASTM F36)	7-12%
» Recovery (ASTM F36)	40%
» Fluid Services**:	Strong acids (Except Hydrofluoric), Steam, Solvents, Hydrocarbons, Chlorine and Cryogenics
» Filler: Silica	
» GYLON [®] 3501-E contains iron oxide (≤ 0,1%)	

* Depending on product and application details.

** See Garlock resistance table.

Installation Recommendation

Please note the information given below is to ensure a long service life and sealing integrity of your gasket.

1 First check

- » Is the selected material suitable for the application?
Do temperature, pressure and medium agree with the process data?
- » Does the gasket have the correct dimensions regarding thickness, inside and outside diameter for the components?
- » Can the bolts deliver the necessary seating stress to the gasket?
- » Has the bolt torque been correctly calculated?

Garlock will calculate the correct torque levels upon request.

2 Before installation

- » Remove old gasket, and clean flange surface of all debris. For best results, use a metal flange scraper, an aerosol gasket remover and a wire brush, suitable for the flange, then inspect the flange for damage. Be sure surface finish and flatness are satisfactory.
- » Use the thinnest possible gasket. However, flanges that are warped, bowed or severely pitted require thicker gaskets.
- » Whenever possible, on metric flanges, use ring gaskets. Full face gaskets have more surface area, requiring additional compressive load on the gasket.
- » Never use metal-based anti-seize on gaskets, since particles may accumulate in the surface imperfections, thereby creating a flange surface that is too smooth to be effective. Such coatings will also greatly impair the resistance of the gasket pressure.

3 Installation

- » Center the gasket on the flange. This is extremely vital where raised faces are involved.
Note: Standard ANSI ring gaskets, when properly cut, should center themselves when the bolts are in place.
- » Use a torque wrench and well-lubricated fasteners with hardened flat washers to ensure correct initial loading.
- » Tighten bolts to compress gasket uniformly. This means going from side to side around the joint in a star-like crossing pattern.
- » All bolts should be tightened in one-third increments, according to proper bolting patterns.
 - A) initially to 30% of the specified torque
 - B) 2nd step to 70% of the specified torque
 - C) 3rd step to 100% of the specified torque
 - D) 4th step round clockwise with 100% torque
- » We do not recommend retorquing pressurized systems. Retorques should be performed on room temperature (non-pressurized) systems 12-24 hours after initial installation.
- » All applicable safety standards including lockout/tagout procedure should be observed.
- » Never use liquid or metallic based anti-stick or lubricating compounds on the gaskets. Premature failure could occur as a result.

Sealing characteristics in accordance with DIN EN 13555:12-2004

		Test Method	Unit	GYLON® Style 3501-E 2,0 mm	GYLON® Style 3504 2,0 mm	GYLON® Style 3510 2,0 mm
Maximum load during installation $Q_{s \max}$	20 °C	EN 13555	MPa	230	200	200
	150 °C	EN 13555	MPa	180	80	160
	200 °C	EN 13555	MPa	180	80	140
	250 °C	EN 13555	MPa	140	60	100
Minimum load during installation Q_{\min} (L = 0,01)	10 bar	EN 13555	MPa	15	13	10
	40 bar	EN 13555	MPa	19,5	13,2	16
	80 bar	EN 13555	MPa	30	20	20
Minimum load during operation $Q_{s \min}$ (L = 0,01)		EN 13555	MPa (10, 20 and 40 bar)	<10	<5	<20
Maximum sealant class $T_{p=20^\circ C, p=40 \text{ bar}}$		EN 13555	L[mg/(s*m)]	1,0x10E-05	1,0x10E-04	1,0x10E-05

(L) = Sealability rate

Note:
Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury. Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing. While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues. Subject to change without notice GARLOCK is a registered trademark for packings, seals, gaskets, and other products of Garlock.
© Garlock Inc 2021. All rights reserved worldwide.

GARLOCK GMBH

an Enpro Company

Falkenweg 1, 41468 Neuss, Germany

+49 2131 349 0

garlockgmbh@garlock.com

www.garlock.com

Garlock Sealing Technologies

Garlock USA

Garlock Australia

Garlock Canada

Garlock China

Garlock Germany

Garlock India

Garlock de México

Garlock New Zealand

Garlock Singapore